

可とう軟銅撚線 規格：JCS1222 素線径0.05m/m

公称断面積	計算断面積	構成	外径	概算重量
〈 sq〉	〈 sq〉	撚り線 / 本数	〈 mm〉	〈 kg/km〉
0.1	0.1	3/17	0.45	0.93
0.2	0.2	3/34	0.65	1.85
0.3	0.3	3/51	0.8	2.78
0.4	0.4	7/29	0.85	3.69
0.5	0.49	7/36	0.9	4.58
0.75	0.76	7/55	1.15	6.99
1	0.98	7/72	1.3	8.39
1.25	1.25	7/91	1.55	11.6
1.4	1.4	7/102	1.6	13.4
2	2	7/146	1.9	19.1
2.5	2.5	7/182	2.2	23.6
3	3.02	7/220	2.4	28.5
3.5	3.5	7/255	2.6	32.4
4	4.01	7/292	2.8	38.2
4.5	4.51	7/328	3	42.1
5.5	5.5	7/400	3.4	51.3
6.5	6.53	7/7/68	3.6	63
8	7.98	7/7/83	4	78.5
10	10	7/7/104	4.4	97.7
12	12.02	7/7/125	5.1	113.3
14	14.04	7/7/146	5.7	136.8
16	16.06	7/7/167	5.9	156.5
20	20	7/7/208	6.7	194.9
22	22.12	7/7/230	7	215.6
30	30.02	19/7/115	5.1	113.3
38	38.11	19/7/146	9.5	373.7
50	50.11	19/7/192	10.5	488.9
54	54.03	19/7/207	11.2	527.1

※実数値は単線径の交差、製造諸条件により変化いたします。

可とう軟銅撚線 規格：JCS1222 素線径0.08m/m

公称断面積	計算断面積	構成	外径	概算重量
〈 sq〉	〈 sq〉	撚り線 / 本数	〈 mm〉	〈 kg/km〉
0.1	0.1	3/7	0.45	0.93
0.2	0.2	3/13	0.65	1.85
0.3	0.3	3/20	0.85	2.79
0.4	0.41	3/27	0.9	3.76
0.5	0.5	3/33	1	4.6
0.75	0.75	3/50	1.2	6.97
0.9	0.91	7/26	1.3	8.46
1.25	1.25	7/36	1.55	11.7
1.4	1.4	7/40	1.6	13.7
2	2	7/57	1.9	18.5
2.5	2.5	7/71	2.2	23.1
3	3.02	7/86	2.4	28.5
3.5	3.5	7/100	2.6	32.5
4	4.01	7/114	2.8	38.2
4.5	4.51	7/127	3	42.1
5.5	5.5	7/157	3.4	51.3
6.5	6.53	7/184	3.6	61.5
8	7.98	7/228	4	75.2
10	10	7/284	4.4	94.11
12	12.02	7/7/49	5.1	113.3
14	14.04	7/7/57	5.7	132.3
16	16.06	7/7/65	5.9	151.3
20	20	7/7/82	6.7	188.4
22	22.12	7/7/90	7	208.4
30	30.03	7/7/122	8.2	280.3
38	38.16	7/7/155	9.5	374.2
50	50.11	19/7/75	10.5	488.9
60	60.14	19/7/90	12	592.8
80	80.18	19/7/120	13.5	798.8
100	100.22	19/7/150	15.5	1004.7

※実数値は単線径の交差、製造諸条件により変化いたします。

可とう軟銅撚線 規格：JCS1222 素線径0.1m/m

公称断面積	計算断面積	構成	外径	概算重量
〈 sq〉	〈 sq〉	撚り線 / 本数	〈 mm〉	〈 kg/km〉
0.4	0.4	3/17	1	3.8
0.5	0.49	3/21	1.1	4.5
0.75	0.75	3/32	1.3	7
0.9	0.88	7/16	1.4	8.4
1.25	1.26	7/23	1.5	12
1.4	1.37	7/25	1.7	13
2	1.98	7/36	1.9	18.3
2.5	2.53	7/46	2.2	23.1
3.5	3.52	7/64	2.6	32.5
4	3.96	7/72	2.8	36.6
4.5	4.51	7/82	3	41.7
5.5	5.5	7/100	3.4	51
6.5	6.55	7/119	3.6	60
8	8.03	7/146	4	73
10	10	7/180	4.4	91
12	11.93	19/80	5.1	112.5
14	14.04	7/7/37	5.7	134
16	16.15	7/7/42	5.9	152.1
20	20	7/7/52	6.7	195.8
22	21.9	7/7/57	7	214.4
30	30	7/7/78	8.2	295.8
38	38.08	7/7/99	9.5	373.4
50	50	7/7/130	10.5	487.9
60	60	7/7/156	12	591.5
80	80	7/7/208	13.5	797
100	100	7/7/260	15.5	1000

※実数値は単線径の交差、製造諸条件により変化いたします。

可とう軟銅撚線 規格：JCS1222 素線径0.12m/m

公称断面積	計算断面積	構成	外径	概算重量
〈 sq〉	〈 sq〉	撚り線 / 本数	〈 mm〉	〈 kg/km〉
1.25	1.26	7/16	1.55	11.6
2	1.98	7/25	2	18.3
3.5	3.48	7/44	2.7	32.2
4	3.96	7/50	3	36.6
5.5	5.54	7/70	3.5	51.2
6.5	6.49	7/82	3.6	60
8	8	7/100	4	73
10	9.98	7/126	4.6	92
14	14.4	7/7/26	5.7	135
16	16.15	7/203	5.9	157.4
20	19.94	7/7/36	6.8	195.8
22	22.17	7/7/40	7.1	217
30	29.92	7/7/54	8.4	295
38	38.24	7/7/69	9.5	375
50	50.22	7/7/90	11	490
60	59.85	7/7/108	12	590
80	79.8	7/7/144	13.5	795
100	99.75	7/7/180	15.5	1000
150	150.34	19/7/100	20	1507.1

※実数値は単線径の交差、製造諸条件により変化いたします。